

Review

Nanoparticle–Biofilm Interactions: The Role of the EPS Matrix

Stephanie Fulaz,¹ Stefania Vitale,¹ Laura Quinn,¹ and Eoin Casey^{1,*}

The negative consequences of biofilms are widely reported. A defining feature of biofilms is the extracellular matrix, a complex mixture of biomacromolecules, termed EPS, which contributes to reduced antimicrobial susceptibility. EPS targeting is a promising, but underexploited, approach to biofilm control allowing disruption of the matrix and thereby increasing the susceptibility to antimicrobials. Nanoparticles (NPs) can play a very important role as ‘carriers’ of EPS matrix disruptors, and several approaches have recently been proposed. In this review, we discuss the application of nanoparticles as antibiofilm technologies with a special emphasis on the role of the EPS matrix in the physicochemical regulation of the nanoparticle–biofilm interaction. We highlight the use of nanoparticles as a platform for a new generation of antibiofilm approaches.

An Introduction to Biofilms and Nanoparticles

Adhesion of bacteria to surfaces and subsequent production of extracellular polymeric substances (EPS) (see [Glossary](#)) prompts the formation of surface-related bacterial communities called **biofilms** [1]. The negative consequences of biofilms include their defining role in an extensive variety of infections [2] and their role in the **biofouling** of surfaces which has negative impacts in the process industries. The prevalence of biofilms and the pathogenesis of biofilm-related infections, for the most part, originate from the capacity of microorganisms to colonize surfaces. Bacteria are equipped to live at the solid–liquid interface by means of their capacity to use flagella, pili, exopolysaccharides, and other adhesive components. Bacterial biofilms have been widely investigated in the context of medical-device-related infections, dental plaque, cystic fibrosis, marine surfaces, natural aquatic systems, water and wastewater processes, and on soil particles [2].

The physical, chemical, and biological complexity and dynamics of biofilm behavior have hampered our full comprehension of why unwanted biofilms are poorly susceptible to **antimicrobial** agents. There are concerns that long-term **antibiotic** use may contribute to the emergence of multidrug-resistant strains [3]. The discovery and development of new classes of antibiotics have been slow [4], hence, the development of alternative approaches is becoming essential. Recently, the potential to exploit **nanoparticles (NPs)** for biofilm eradication or control has taken hold. The advantage of NPs lies in their intrinsic high surface-area-to-volume ratio, providing a platform for the development of materials with a wide spectrum of mechanical, chemical, electrical, and magnetic properties [5]. Such materials include metal/metal oxide NPs [6,7], nanocapsules [8], polymeric NPs [9], liposomes [10], nanoenzymes [11], and hydrogels [12]. The description of specific classes of NPs is beyond the scope of this review [13–15].

The development of functional NPs with the capacity to transport antimicrobial agents to the target site and release them in a controlled way is advantageous due to a potential reduction in toxicity and an increase in drug efficacy [16,17]. Furthermore, **nanocarriers** have been shown to enhance the penetration of antimicrobial agents inside the matrix [18]. However, this matrix, the so-called ‘dark matter’ of biofilms [19] is a complex material, and while some progress has been reported in its characterization [20,21] a key challenge is its chemical and physical variability and heterogeneity. In the context of biofilm control, while the antimicrobial effects of NPs have been already established, the factors influencing their interaction with the biofilms are poorly understood with respect to the role of the EPS matrix. A fundamental understanding of the NP–EPS interaction would therefore improve our ability to design more effective antibiofilm strategies. This review describes the interactions between NPs and EPS components of the **biofilm matrix**, considering physicochemical interactions, as well as the applications of nanotechnology in biofilm prevention or eradication.

Highlights

Self-adhering bacterial communities embedded in a matrix of hydrated macromolecules, known as biofilms, are prevalent and widespread. The matrix offers protection to the bacteria, reducing the cell susceptibility to antimicrobials.

Functional nanoparticles are a promising technology to control or eradicate biofilms, providing the ability to enhance antimicrobial transport to the cell vicinity or alternatively to carry matrix dispersion agents.

Critical to the development of novel strategies to control biofilm infections is an in-depth knowledge of the biofilm matrix which is still poorly understood due to its spatial and chemical variability and complexity

A fundamental understanding of NP–EPS interactions has the potential to improve our ability to design more effective antibiofilm strategies.

¹School of Chemical and Bioprocess Engineering, University College Dublin (UCD), Belfield, Dublin 4, Ireland

*Correspondence: eoin.casey@ucd.ie



Biofilms and the Biofilm Matrix

Biofilms are widespread, dynamic, structurally complex, integrated multicellular communities of surface-adhering microorganisms that are embedded within an extracellular polymeric matrix [22,23]. Biofilm formation can be seen as a mode of growth which provides protection to the cells, therefore allowing them to survive in hostile environments [24]. This formation can be influenced by cellular, surface, and environmental factors. These factors include microbial species, the availability of nutrients, surface composition and roughness, cell motility, temperature, hydrodynamics, and hydrophobicity [25]. Furthermore, recent advances in molecular biology and microscopy have revealed that social interactions have vital roles in mediating the responses of bacteria to their environment [26].

The production of the biofilm matrix is one of the key stages in biofilm formation (Figure 1). The matrix provides crucial architectural support and protection for the microbial communities that it surrounds and is composed of EPS [20,27]. In the majority of cases, the matrix comprises 90% of the biofilm mass, with microorganisms accounting for the remainder [20]. Although the physical and chemical composition of the EPS varies between species, it is mainly composed of polysaccharides, proteins, lipids, and extracellular DNA (eDNA) [28,29], as described in Box 1. The EPS comprises a network of diverse macromolecules [30]. For a more detailed discussion on this specific topic we refer the reader to Flemming *et al.* [31].

Nanoparticle–Biofilm Transport Phenomena

Interactions between NPs and biofilms (Figure 2) can be described by three essentially sequential mechanisms [32]: transport of NPs to the biofilm–fluid interface; attachment to the biofilm surface (outer region); and migration within the biofilm.

It is important to note that biofilms are dynamic entities, with their structure and material/chemical properties continuously mediated by biochemical and physicochemical factors which are, in turn, influenced by the local environmental conditions [33]. This interplay adds to the complexity of NP transport into biofilms. In general, the relative self-diffusion coefficients decrease exponentially with the radius of the NP [34]. However, their transport is also affected by the EPS matrix viscosity, cell density, liquid flow, external mass transfer resistance, physicochemical interactions of the NPs with EPS components, and the characteristics of the water spaces (pores) within the EPS matrix [35].

It is essential to understand how NPs interact with and behave in biofilms in order to rationally develop improved functional nanomaterials. To date, most published research in this field has focussed on the antimicrobial efficacy of drug delivery nanocarriers, while only few studies have examined the fundamentals of NP transport phenomena in biofilms.

To eradicate unwanted bacterial biofilms, it seems rational that functional NPs should penetrate the entire matrix. The initial step of penetration in the EPS matrix is mostly controlled by the size of the NPs [34], whereas the interactions with EPS components are governed by the NP's surface properties (charge and functional groups). When NPs come into contact with an environment containing organic molecules, a corona-like coating is formed on the NP surface, and the nature of this corona influences the NP–biofilm interactions [32]. In the matrix, different biomolecules, such as proteins, polysaccharides, nucleic acids, lipids, and metabolites can adsorb on the NP surface [36].

Nanoparticle–Biofilm Interactions

The physicochemical characteristics of the NPs (size, shape, surface charge, hydrophobicity, and functional groups) determine their interaction with biofilm components, both in the EPS matrix and on the bacterial surface [37–39]. NPs remain pristine in any biological environment for only very short timescales [32,40]. On first coming into contact with a biofilm, NPs inevitably interact with a complex mixture of **macromolecules** that alters their surface properties, and the different properties are ascribed to the so-called '**biomolecular corona**' [41,42], often referred to as a '**protein corona**' [43]. The mechanisms of protein corona formation are not yet fully elucidated, but several studies have shown that its composition and evolution are correlated to both the NP properties (size, shape,

Glossary

Antibiotic: an antimicrobial substance with the ability to kill bacteria or inhibit bacterial growth.

Antimicrobial: (noun) an agent or drug that kills microorganisms or stops their growth, (adjective) active against microorganisms.

Biofilm: an aggregate of surface-adhering microorganisms that are embedded within an extracellular polymeric matrix.

Biofilm matrix: self-produced hydrated matrix of extracellular polymeric substances (EPS) composed of several (bio)molecules (proteins, carbohydrates, lipids, and nucleic acids).

Biofouling: unwanted growth of microbial communities on artificial surfaces in aquatic environments.

Biomolecular corona: adsorption of biomolecules onto an inorganic surface, such as nanoparticles.

The biomolecules form a coating wrapping around the nanoparticle and changing its characteristics (size, charge, surface).

Electrostatic interactions: interactions between objects with an intrinsic charge; they can be repulsive (same charge) or attractive (opposite charge).

EPS: extracellular polymeric substances (polysaccharides, proteins, lipids, and extracellular DNA) produced by microorganisms during biofilm formation. It is responsible for the integrity and structure of the biofilm and can also act as a protective barrier.


Hydrophobic interactions: the interactions between water and hydrophobes (low-water-soluble molecules, normally with a long carbon chain), which causes nonpolar species to aggregate in water.

Ionic strength: a measure of the concentration of ions in a solution; it represents the strength of the electrical field in this solution.

Macromolecules: large molecules consisting of monomers joined by covalent bonds, such as proteins, carbohydrates, lipids, and nucleic acids.

Nanocarriers: nanomaterials used to transport another substance, such as a drug.

Nanoparticles (NPs): particles that have at least one dimension under 100 nm.



Trends in Microbiology

Figure 1. Life Cycle of Biofilm.

(A) Attachment/adherence of the bacteria to the surface. (B) Formation of monolayer and production of extracellular polymeric substances (EPS). (C) Microcolony formation and proliferation. (D) Biofilm dispersal-detachment and reversion of planktonic cells. (E) Start of life cycle of biofilm again.

surface charge and curvature, functionalization) and the biological characteristic of the medium (concentration, topology, ratio of physiological media to NPs' concentration) [43]. While the formation of the protein corona and its effect on the NPs' interactions are extensively reported in the biomedical context (e.g., blood plasma), a comprehensive investigation of the NP-protein corona in biofilms is lacking [43]. In this context, it must be pointed out that also another kind of corona can be formed on NPs released into the environment, namely, a natural organic matter (NOM) corona [32,43,44]. The complexity of the biofilm, together with the complex nature of the NP corona, further adds to the difficulty in generalizing the nature of biofilm-NP interactions.

Physicochemical Characteristics (or Properties) Influencing the Nanoparticle-Biofilm Interaction

The interaction between (engineered) NPs and bacterial biofilms is modulated by the physicochemical properties of both the particles and biofilm (Figure 3) [45]. These properties and their interactions determine the degree of particle uptake, the specificity of interaction with both the biofilm matrix and bacterial cells, and in some cases, the toxicity mechanism. The exact role, extent, and mechanism of each interaction is not yet fully understood because they take place in a dynamic physiological context whereby a cascade of collateral phenomena can be triggered from a single specific interaction. For instance, it has been established that the simple adsorption of NPs on the cell surface can lead to physical damage of the cellular membrane as well as production of **reactive oxygen species (ROS)**; the latter can, in turn, negatively affect the cell metabolism (e.g., through inhibition of mitochondrial activity, protein production, DNA synthesis, etc.) [46]. Although there is ample evidence from the scientific literature that bacteria in the 'biofilm phenotype' are more resistant to antimicrobial agents than their planktonic counterpart [24,47], and that this increased **resistance** is largely caused by the EPS matrix protecting the cells, the research directed to the study of the antimicrobial action of NPs often has not taken into account the interaction between the NP and the matrix, but has instead focused almost exclusively on the NP-cell interaction [40,48]. Furthermore, the likely occurrence of (protein) corona adsorption around the NPs in the EPS matrix can modulate the interaction of the particles with the biofilm; in spite of this, the corona formation for NPs inside the biofilm matrix has not yet been discussed.

Despite the complexity of bacterial biofilms [31], some general observations can be described about the main physicochemical factors that dictate the NP-biofilm interaction. The most important interactions are electrostatic, **hydrophobic**, and **steric**. These are mainly physical interactions, although also chemical and biological interactions can take place between the EPS matrix and NPs [49]. In general, **electrostatic interactions** are of paramount importance in the regulation of biofilm formation, in

Reactive oxygen species: chemical compounds containing oxygen that easily react with other molecules, also known as free radicals.

Resistance: the ability of a microorganism to prevent the action of an antimicrobial to act against it.

Steric interactions: effects resulting from repulsive forces between overlapping electron clouds of molecules.

Box 1. EPS Components and Their Function in the Biofilm

Polysaccharides play a fundamental role in the biofilm's matrix [91]; some of the most common polysaccharides are cellulose, Psl, Pel, alginate, and the staphylococcal polysaccharide intercellular adhesin (PIA) [92–95]. Proteins also play a critical role, and in some cases are present at higher concentrations than polysaccharides [96]. Common proteins present in the matrix are amyloid fibers [97]. TasA, Tap A, and Sip W, which are all functional amyloid fibers, aid in the cell–cell adhesion during biofilm formation [98–101]. BslA is a cell-surface-associated amphiphilic protein which can form a protective barrier on the surface of *Bacillus subtilis* biofilms, thereby providing protection against environmental stressors [102]. A proteomic study of proteins present in the *Pseudomonas aeruginosa* biofilm indicated that roughly 30% of the matrix proteins were external membrane proteins, normally found in outer-membrane vesicles (OMVs), while some proteins were derived from secreted proteins and lysed cells [103].

Previous studies have suggested that eDNA plays an important role in the formation, structural stability, and integrity of bacterial biofilms [104,105].

As previously stated, the EPS has been called 'the dark matter of biofilms' [19] and therefore can provide a number of challenges in the development of EPS-targeting therapeutics and biofilm-eradication methods due to the complexity and variability of the components of the EPS and the interactions between these components. Examples of the EPS components and their role in biofilm formation are listed in detail in Table I.

the first step of adhesion to surfaces, and following cohesion of the EPS matrix [20,50]. Furthermore, hydrophobic interactions play a major role in the context of biofilm formation and subsequent regulation [31,51]. Steric interactions are important, particularly for the colloidal stabilization of the NPs: steric stabilization can prevent NP aggregation, even in media with high salinity or ionic strength, and this is very important in determining the interaction with the biofilm EPS [49]. It is important to note that the overall interaction is often determined by a combination of forces, and in the complex biofilm matrix the establishment of the extent of contribution of each factor is nontrivial.

In general, positively charged NPs are more likely to interact with the EPS substances (polysaccharide skeleton, proteins, humic and uronic acids, and DNA) having, on the whole, a negative charge [52], and also with the generally negatively charged bacterial cell wall [53]. Rotello and coworkers studied the different interactions of an *Escherichia coli* biofilm with, respectively, neutral, anionic, and cationic quantum dots (QDs) ($d = 7.5\text{--}24\text{ nm}$) [54], reporting that, after 1 h of incubation in 72-h biofilms, both neutral and anionic QDs were not able to penetrate within the biofilm, while cationic ones were able to penetrate and diffuse within the matrix. Furthermore, they also reported a different localization for hydrophilic cationic QDs and hydrophobic cationic ones. The hydrophilic particles were not colocalized with the bacteria, indicating interaction with only the EPS, whereas the hydrophobic ones were colocalized with the bacteria. These data suggest that a synergistic action of both surface charge and functional groups, not only the net charge, might determine the specific interactions with the biofilm components.

With regard to hydrophobic interactions, Mitzel *et al.* [55] analyzed the interaction of carboxylate- and sulfate-modified polystyrene latex NPs ($d = 20\text{ nm}$) with two *P. aeruginosa* engineered strains, one with hydrophilic cell walls and the other hydrophobic. It was shown that the interaction was much stronger between NPs and hydrophobic bacterial cells within the biofilm, rather than the hydrophilic ones. The effect of ionic strength on the NP retention was investigated, showing that the retention of the hydrophobic particles was not influenced by it; and it was hypothesized that this greater stability against increase in ionic strength could be due to hydrophobic EPS components acting as stabilizers.

Manipulation of the electrostatic forces occurring in the context of NP–biofilm interactions is another interesting topic. In a very recent paper, Harper *et al.* [56] reported that the screening of the electrostatic forces within the EPS can be exploited to enhance the diffusion of nanomaterials within the biofilm. The authors used alpha tocopherol phosphate (α -TP) liposomes ($d = 700\text{ nm}$) as antimicrobial nanomaterial, against oral biofilm *Streptococcus oralis*. The α -TP liposomes have a negatively charged surface, and the data presented show that they are administered to the biofilm using a phosphate buffer (negative electrolyte) as they are not able to penetrate inside the matrix; instead, if Tris

Component	Examples	Function	Refs
Proteins	TasA, TapB, BslA, SipW, CdrA, lectins	<ul style="list-style-type: none"> ● Adhesion ● Aggregation ● Cohesion ● Structural integrity ● Protective barrier ● Enzymatic activity ● Electron donor or acceptor 	[20,27,28,97,98,102,106–108]
Polysaccharides	Pel, Psl, PIA, alginate, cellulose	<ul style="list-style-type: none"> ● Adhesion ● Aggregation ● Cohesion ● Protective barrier ● Structural integrity ● Water retention ● Binding of enzymes 	[92–95,109,110]
eDNA		<ul style="list-style-type: none"> ● Adhesion ● Aggregation ● Cohesion ● Structural integrity ● Structural stability ● Intercellular connector 	[20,27,99–101,104,105,111]


Table 1. Components of Extracellular Polymeric Substances (EPS) in Biofilms and Their Function in Biofilm Formation and Development

buffer (positive electrolyte) is used, the liposomes can diffuse inside the biofilm, with no modification of their negative surface charge. This is evidence that the positive electrolytes of the buffer are able to screen the electrostatic repulsion that occurs between the negatively charged liposome and the EPS components (negatively charged on the whole). The consequent minimization of the electrostatic repulsion allows the α -TP liposomes to diffuse in the matrix and reach the target cells.

However, steric stabilization of the NPs with ligands such as negatively charged poly(vinylpyrrolidone) (PVP) can also contribute to the overall interaction through electrostatic phenomena. For instance, Mitzel and Tufenkji [57] reported a very low adsorption of PVP-capped silver NPs (AgNPs, $d = 78$ – 134 nm) onto *P. aeruginosa* biofilms. This was attributed to repulsive electrostatic forces between the negatively charged chains of PVP and the EPS polysaccharides of the biofilm. Steric interactions in the biofilms can also be a determining factor in the availability and consequent toxicity of NPs. Adeleye et al. studied the stability of various copper-based NPs ($d = 40$ – 50 nm) in an aqueous environment in the presence or absence of EPS, extracted from *Isochrysis galbana* marine phytoplankton [58]. It was shown that the EPS interacts with the copper nanomaterials by sterically stabilizing them, so that less aggregation occurs in comparison with the same nanomaterials in a solely buffer solution.

The above discussed NP–biofilm interactions clearly show the complex nature of the interaction itself; an additional complication is given by the fact that the NPs and their properties can affect the bioentities that they are in contact with, but they can also be ‘transformed’ as a consequence of the interaction [59], undergoing chemical, physical, or biological transformations that are rarely easy to predict. All of these potential interactions are relevant to NP-based antibiofilm technologies.

In the following section, several examples of NP-based antibiofilm strategies are presented and discussed.



Trends in Microbiology


Figure 2. Representation of the Stages (Transport, Initial Deposition, and Migration) Involving Nanoparticle (NP) Transport Phenomena within Bacterial Biofilms.

As NPs are incorporated in the matrix, sorption (and sometimes reactive) processes result in their surface becoming covered in biofilm matrix constituents, a corona structure. This process changes NPs' properties (composition, size, charge, surface functionality). NPs interact differently with distinct biomolecules, and these interactions are influenced by the environment where NP–biomolecules are inserted, such as the complex extracellular polymeric substances (EPS) matrix. A myriad of different interactions affect the transport of NPs in the matrix, due to the complex physicochemical composition of the EPS.

Nanoparticles as Tools for Biofilm Control and Eradication

Bacterial cells embedded in a biofilm are inherently more resistant to host immune responses and antibacterial chemotherapy compared to planktonic cells [24]. Proposed mechanisms for this include: reduced penetration of antimicrobials into the biofilm; inactivation of antimicrobial agents by EPS components; and the altered metabolic state of bacterial cells within the biofilm [31,60]. The EPS physicochemical complexity, its variability, and its component interactions make the treatment of biofilm infections a significant challenge for therapeutics [28]. New biofilm therapies, such as functional NPs, will need to focus on the whole microenvironment in order to be successful [61] and be resistant to adverse reactions [24]. An additional challenge for purely antimicrobial approaches relates to the fact that biofilm EPS components remain in place even after microbial inactivation/death. The remaining EPS matrix may facilitate subsequent colonization by other microorganisms [28], with significant consequences; for example, the *in vivo* dispersal of biofilm bacteria in the absence of antibiotic therapy was reported to cause lethal septicemia in a mouse wound model [62]. Prospective biofilm dispersal agents for clinical application consequently will require careful safety evaluation and should be administered alongside antibiotics to prevent recolonization [28].

Two broad strategies to counteract unwanted biofilms are the prevention or minimization of initial adhesion (passive strategy) and antimicrobial approaches (active strategy) [63]. Developments in anti-fouling surfaces are reviewed elsewhere [64]. Another important area is the development of



Trends in Microbiology

Figure 3. Graphical Diagram Describing the Different Physicochemical Interactions between Nanoparticles (NPs) and Bacterial Biofilms.

antimicrobial coatings for wound dressings and implants [65]. Wound dressings functionalized with antimicrobial moieties have been shown to prevent microbial colonization [66]. The most common example is the use of AgNPs which often demonstrate an improved inhibitory activity of microbial colonization, adhesion, and biofilm growth.

Nanotechnology has opened up the possibility for the design of sophisticated drug-delivery systems. The potential exists to use nanocarriers to penetrate the biofilm and, for example, they can be designed to protect the active ingredient from enzymatic inactivation or binding to the biofilm matrix or other components surrounding the biofilm infection site [67]. The encapsulation of antibiotics in organic NPs can provide increased antimicrobial potency compared to free antibiotics [68,69]. The immobilization of antimicrobial and antibiofilm agents in nanomaterials provides an alternative path to overcome payload degradation, poor delivery of water-insoluble molecules, deficient drug uptake, excessive drug efflux, and resistance development [70].

Lipid and polymer NPs are of major interest due to their biocompatibility, versatility, potential as platforms for targeted/triggered release, and ability to incorporate lipophilic as well as hydrophilic drugs.

Lipid NPs or liposomes can fuse with phospholipid membranes and deliver the antibiotic directly to the cells thereby maximizing therapeutic benefit while reducing unwanted side effects [67]. Several liposomal formulations for the treatment of biofilm infections are under development, but, to the best of our knowledge, currently no such products are on the market. Arikace™ (Transave, Inc.) a liposomal formulation containing the antibiotic amikacin is in Phase III clinical trials [71], and Fluidsomes™, containing tobramycin, is in a Phase II trial for the treatment of cystic fibrosis-associated respiratory infections [67,72].

Drug-delivery NPs with targeting ligands have potential for promoting enhanced proximity between the nanocarrier and individual bacterial cells within the matrix. Nonspecific targeting relies on charge-based interactions and hydrogen bonding of the nanocarrier with the biofilm; specific targeting is based on targeting ligands that selectively bind to a target molecule inside the biofilm. For instance, poly(ethylene)glycol–poly(b-amino esters) (PEG–PAE) micelles ($d = 100$ nm) conjugated with Triclosan were able to penetrate biofilms and target bacterial cell surfaces [73]. Once in the low-pH environment, the degradation of the ester-linkage with PAE by bacterial lipases leads to the release of Triclosan. This targeted delivery of Triclosan was shown to enhance the antimicrobial potency against MDR *Staphylococcus aureus*, *E. coli*, and streptococcal biofilms compared to free antimicrobial controls. Similarly, polymer NPs based on a triblock copolymer poly(D,L-lactic-co-glycolic acid)–b-poly(L-histidine)–b-PEG (PLGA–PLH–PEG) ($d = 196$ nm) loaded with vancomycin selectively bound to bacterial cells in acidic conditions owing to their pH-sensitive surface charge switching [74]. The nanocarrier showed pH-responsive antibacterial efficiency. Such an approach seems promising for the systematic development of drug carrier's to target and treat Gram-positive, Gram-negative, or polymicrobial infections.

Several types of inorganic NPs have been shown to exhibit antimicrobial properties. The antibacterial activity of gold [75] and AgNPs [76–79] has been extensively reported. Although several studies have been conducted on the inhibitory effect of AgNPs on bacterial biofilms, the interactions between bacterial biofilms and AgNPs is not fully understood. Extensive sloughing of the biofilm bacteria into suspension was associated with NP–bacterial interactions but with very little change in bacterial viability. AgNP aggregates were detected in the EPS matrix, suggesting a mechanism for the lack of efficacy of biofilm eradication. Although the reasons for the effect of NPs ($d = 5$ – 150 nm) on biofilm detachment were not apparent, the data suggested that exposure time played an important role, with significantly less biomass detaching after exposure over 8–24 h periods compared to initial exposure [80]. Another study compared AgNP ($d = 15$ – 21 nm) treatment between biofilm and planktonic cells where it was shown that biofilms were about four times more resistant to AgNP inhibition than planktonic cells [81]. The effect was partly attributed to NP aggregation, due to changes in ionic strength and interactions with complexing agents from the EPS, together with retarded silver particle/ion diffusion within the biofilm matrix. AgNPs ($d = 5$ – 106 nm) interactions with wastewater biofilms in their natural environment have also been investigated [82]. Biofilm bacteria, treated as isolated pure culture, were much more sensitive to AgNPs, compared with mixtures of bacteria in the biofilm. EPS was believed to provide physical protection for bacteria under AgNP treatment. When loosely bound EPS from bacterial biofilms was removed, they were more sensitive to AgNPs.

The EPS matrix is a complex mixture, with spatial and temporal variations dependent on several factors such as microbial physiology, environmental conditions (fluid chemistry, temperature), nutrient availability, and hydrodynamics. Targeting the EPS is a vital but still underexploited approach for biofilm control, allowing for the disruption of the matrix and potentially increasing the cell susceptibility to antimicrobial strategies. NPs can play a very important role as 'carriers' of EPS matrix disruptors, and several approaches have been proposed [64,83,84].

A promising strategy consists of using engineered NPs as carriers for specific quorum sensing (QS) inhibitors. A significant reduction of cell-to-cell communication was observed when β -cyclodextrin-functionalized silica NPs ($d = 15$ and 50 nm) were added to *Vibrio fischeri* cultures; β -cyclodextrin is a nonspecific binding agent for acylhomoserine lactones (HSLs) signaling molecules [13]. Silver [85,86] and AgCl-loaded TiO_2 NPs ($d = 6$ – 7 nm) [87] have also been successfully exploited to inhibit

QS in *P. aeruginosa*, *Chromobacterium violaceum*, *Serratia marcescens*, and *E. coli* biofilms. Zinc NPs (ZnNPs, $d = 24$ nm), synthesized from *Nigella sativa* seed extract, demonstrated broad-spectrum QS inhibition in *C. violaceum* and *P. aeruginosa*. Elastase, protease, pyocyanin, and alginate production were significantly inhibited. Subinhibitory concentrations of ZnNPs were able to inhibit the biofilm formation and disperse preformed mature biofilms of *C. violaceum*, *P. aeruginosa*, *Listeria monocytogenes*, and *E. coli* [88].

Other promising approaches to disrupt the EPS include the use of enzyme-functionalized NPs or enzyme mimicry. Gold-based NPs ($d = 25$ nm) and silica-based nanobeads ($d = 501, 638$ nm) functionalized with proteinase K were effective in disrupting the structure of *Pseudomonas fluorescens* biofilms, decreasing surface coverage and thickness [89,90]. This reusable enzyme-functionalized nanobead approach could be a cost-effective approach to disperse biofilms compared to free enzymes. A DNase-mimetic artificial enzyme composed of gold NPs with cerium (IV) complexes were immobilized onto the surface of magnetic $\text{Fe}_3\text{O}_4/\text{SiO}_2$ NPs. This artificial nanoenzyme with DNase-like activity exhibited high cleavage ability towards eDNA, with improved stability and easy recovery. Substrates coated with these NPs inhibited bacterial adhesion and biofilm formation for long periods. Additionally, by EPS degradation, the NPs were efficient in the dispersion of established biofilms. Furthermore, the combined use with traditional antibiotics increased the ability to eradicate enclosed bacteria and eliminate biofilms [11].

Concluding Remarks and Future Perspectives

While biofilms are the prevalent form of bacteria in nature [23], their recalcitrance presents a major challenge that has generally not been adequately met by conventional antimicrobials. The self-produced biofilm matrix creates a physically and chemically complex barrier which partly shields the embedded cells from antimicrobial therapy, immune responses, and environmental challenges. The spatial and temporal variability of biofilms, both in terms of chemical and microbial composition, have added a further layer of complexity that has inhibited eradication strategies.

Nanotechnology is a promising route for new antimicrobial and delivery-system approaches, particularly in the context of enhanced penetration and targeted delivery of antimicrobials within the biofilm. Moreover, EPS-targeting strategies allow for matrix disruption, enhancing the susceptibility of the remaining biofilm to antimicrobial therapy.

Although there are some examples of antimicrobial catheters, implants, and wound dressings containing AgNPs available for clinical use, sophisticated antibiofilm strategies are still underdeveloped, with studies mostly focussed *in vitro*, and only two products are currently in clinical trials: Arikace™ (Phase III) and Fluidosomes™ (Phase II) [60,72].

Ultimately, the development of successful strategies to combat biofilms requires a multidisciplinary approach in order to tackle the various challenges that biofilms present (see Outstanding Questions). Engineered NPs represent a very promising tool for the accomplishment of this task; however, it must be stressed that their commercial deployment in certain settings (process plants, healthcare surfaces, etc.) will depend not only on their effectiveness but also on their acceptance from a regulatory perspective in the context of the release of nanomaterials. The assessment of nanomaterial impact on human health and the environment is currently an open debate, and the future commercial development of NP-based biofilm technologies will depend on overcoming such regulatory hurdles.

It is important to note the need for systematic *in vivo* studies to evaluate the effectiveness of these new technologies in the biomedical context. Specificity is a key factor in clinical applications, where it is necessary to distinguish between pathogenic and commensal bacteria and host tissue. Strategies based on smart release by environmental cues, such as pH, oxygen concentration, reducing potential, improve selectivity, and drug delivery. The use of aptamers, antibodies, and peptides also enhances specificity [28]. However, the synthetic route and cost must be considered. Another critical factor to be investigated is how the NPs are modified in the biological milieu, such as blood, and how these

Outstanding Questions

How and why does the EPS composition change under different environmental/growth conditions? Are there specific conditions which trigger the production of certain components?

Why have NP-based antibiofilm technologies not yet been commercialized? What challenges need to be overcome to develop such products? Are the positive benefits of NPs oversold?

What is the ultimate fate of antibiofilm NPs *in vivo* and in the environment?

changes will affect their function. Furthermore, a rigorous assessment of NPs' toxicity and impact on commensals is needed. Future directions should focus on the complete biofilm eradication by addressing simultaneously the EPS matrix and the cells, enhancing the therapeutic effect, while minimizing toxicity and resistance development.

Acknowledgments

This research was supported by Science Foundation Ireland (SFI) under grant number 15/IA/3008.

References

- Costerton, J.W. et al. (1987) Bacterial biofilms in nature and disease. *Annu. Rev. Microbiol.* 41, 435–464
- Costerton, J.W. (1999) Bacterial biofilms: a common cause of persistent infections. *Science* 284, 1318–1322
- Lynch, A.S. and Robertson, G.T. (2008) Bacterial and fungal biofilm infections. *Annu. Rev. Med.* 59, 415–428
- Fischbach, M.A. and Walsh, C.T. (2009) Antibiotics for emerging pathogens. *Science* 325, 1089–1093
- Whitesides, G. (2005) Nanoscience, nanotechnology, and chemistry. *Small* 1, 172–179
- Geilich, B.M. et al. (2017) Superparamagnetic iron oxide-encapsulating polymeric nanocarriers for biofilm eradication. *Biomaterials* 119, 78–85
- Hu, D. et al. (2017) Surface-adaptive gold nanoparticles with effective adherence and enhanced photothermal ablation of methicillin-resistant *Staphylococcus aureus* biofilm. *ACS Nano* 11, 9330–9339
- Duncan, B. et al. (2015) Nanoparticle-stabilized capsules for the treatment of bacterial biofilms. *ACS Nano* 9, 7775–7782
- Nguyen, T.-K. et al. (2016) Co-delivery of nitric oxide and antibiotic using polymeric nanoparticles. *Chem. Sci.* 7, 1016–1027
- Alhariri, M. et al. (2017) Efficacy of neutral and negatively charged liposome-loaded gentamicin on planktonic bacteria and biofilm communities. *Int. J. Nanomedicine* 12, 6949–6961
- Chen, Z. et al. (2016) A multinuclear metal complex based DNase-mimetic artificial enzyme: matrix cleavage for combating bacterial biofilms. *Angew. Chem. Int. Ed.* 55, 10732–10736
- Gao, W. et al. (2014) Hydrogel containing nanoparticle-stabilized liposomes for topical antimicrobial delivery. *ACS Nano* 8, 2900–2907
- Miller, K.P. et al. (2015) Engineering nanoparticles to silence bacterial communication. *Front. Microbiol.* 6, 1–7
- Ealia, A.M.S. and Saravanakumar, M.P. (2017) A review on the classification, characterisation, synthesis of nanoparticles and their application. *IOP Conf. Ser. Mater. Sci. Eng.* 263, 032019
- Jeevanandam, J. et al. (2018) Review on nanoparticles and nanostructured materials: history, sources, toxicity and regulations. *Beilstein J. Nanotechnol.* 9, 1050–1074
- He, Q. et al. (2011) *In vivo* biodistribution and urinary excretion of mesoporous silica nanoparticles: Effects of particle size and PEGylation. *Small* 7, 271–280
- González, B. et al. (2018) Mesoporous silica nanoparticles decorated with polycationic dendrimers for infection treatment. *Acta Biomater.* 68, 261–271
- Hetrick, E.M. et al. (2009) Anti-biofilm efficacy of nitric oxide-releasing silica nanoparticles. *Biomaterials* 30, 2782–2789
- Flemming, H.-C. (2011) The perfect slime. *Colloids Surfaces B Biointerf.* 86, 251–259
- Flemming, H.-C. and Wingender, J. (2010) The biofilm matrix. *Nat. Rev. Microbiol.* 8, 623–633
- Hobley, L. et al. (2015) Giving structure to the biofilm matrix: an overview of individual strategies and emerging common themes. *FEMS Microbiol. Rev.* 39, 649–669
- Stoodley, P. et al. (2002) Biofilms as complex differentiated communities. *Annu. Rev. Microbiol.* 56, 187–209
- Flemming, H.-C. and Wuertz, S. (2019) Bacteria and archaea on Earth and their abundance in biofilms. *Nat. Rev. Microbiol.* 17, 247–260
- Hall-Stoodley, L. et al. (2004) Bacterial biofilms: from the natural environment to infectious diseases. *Nat. Rev. Microbiol.* 2, 95–108
- Li, X.Z. et al. (2007) Single-species microbial biofilm screening for industrial applications. *Appl. Microbiol. Biotechnol.* 76, 1255–1262
- Nadell, C.D. et al. (2016) Spatial structure, cooperation and competition in biofilms. *Nat. Rev. Microbiol.* 14, 589–600
- Flemming, H.-C. et al. (2007) The EPS matrix: The 'house of biofilm cells'. *J. Bacteriol.* 189, 7945–7947
- Koo, H. et al. (2017) Targeting microbial biofilms: current and prospective therapeutic strategies. *Nat. Rev. Microbiol.* 15, 740–755
- Toyofuku, M. et al. (2012) Identification of proteins associated with the pseudomonas aeruginosa biofilm extracellular matrix. *J. Proteome Res.* 11, 4906–4915
- Decho, A.W. and Gutierrez, T. (2017) Microbial extracellular polymeric substances (EPSs) in ocean systems. *Front. Microbiol.* 8, 922
- Flemming, H.-C. et al. (2016) Biofilms: an emergent form of bacterial life. *Nat. Rev. Microbiol.* 14, 563–575
- Ikuma, K. et al. (2015) When nanoparticles meet biofilms – interactions guiding the environmental fate and accumulation of nanoparticles. *Front. Microbiol.* 6, 591
- Petosa, A.R. et al. (2010) Aggregation and deposition of engineered nanomaterials in aquatic environments: role of physicochemical interactions. *Environ. Sci. Technol.* 44, 6532–6549
- Peulen, T.O. and Wilkinson, K.J. (2011) Diffusion of nanoparticles in a biofilm. *Environ. Sci. Technol.* 45, 3367–3373
- Miller, K.P. et al. (2015) Inorganic nanoparticles engineered to attack bacteria. *Chem. Soc. Rev.* 44, 7787–7807
- Stan, M.S. et al. (2018) Dynamic analysis of the interactions between Si/SiO₂ quantum dots and biomolecules for improving applications based on nano-bio interfaces. *Sci. Rep.* 8, 5289

37. Canesi, L. and Corsi, I. (2016) Effects of nanomaterials on marine invertebrates. *Sci. Total Environ.* 565, 933–940
38. Mi, G. et al. (2018) Reducing bacterial infections and biofilm formation using nanoparticles and nanostructured antibacterial surfaces. *Adv. Healthc. Mater.* 7, 1800103
39. Joo, S.H. and Aggarwal, S. (2018) Factors impacting the interactions of engineered nanoparticles with bacterial cells and biofilms: Mechanistic insights and state of knowledge. *J. Environ. Manag.* 225, 62–74
40. Westmeier, D. et al. (2018) Nanomaterial-microbe cross-talk: physicochemical principles and (patho) biological consequences. *Chem. Soc. Rev.* 47, 5312–5337
41. Mu, Q. et al. (2014) Chemical basis of interactions between engineered nanoparticles and biological systems. *Chem. Rev.* 114, 7740–7781
42. Ke, P.C. et al. (2017) A decade of the protein corona. *ACS Nano* 11, 11773–11776
43. Docter, D. et al. (2015) The nanoparticle biomolecule corona: lessons learned – challenge accepted? *Chem. Soc. Rev.* 44, 6094–6121
44. Wirth, S.M. et al. (2012) Natural organic matter alters biofilm tolerance to silver nanoparticles and dissolved silver. *Environ. Sci. Technol.* 46, 12687–12696
45. Lerner, R.N. et al. (2012) The effects of biofilm on the transport of stabilized zerovalent iron nanoparticles in saturated porous media. *Water Res.* 46, 975–985
46. Hajipour, M.J. et al. (2012) Antibacterial properties of nanoparticles. *Trends Biotechnol.* 30, 499–511
47. Natan, M. and Banin, E. (2017) From Nano to Micro: using nanotechnology to combat microorganisms and their multidrug resistance. *FEMS Microbiol. Rev.* 41, 302–322
48. Chen, J. et al. (2017) Integrating recognition elements with nanomaterials for bacteria sensing. *Chem. Soc. Rev.* 46, 1272–1283
49. Huangfu, X. et al. (2019) A review on the interactions between engineered nanoparticles with extracellular and intracellular polymeric substances from wastewater treatment aggregates. *Chemosphere* 219, 766–783
50. Habimana, O. et al. (2014) The role of cell-surface interactions in bacterial initial adhesion and consequent biofilm formation on nanofiltration/ reverse osmosis membranes. *J. Membr. Sci.* 454, 82–96
51. Renner, L.D. and Weibel, D.B. (2011) Physicochemical regulation of biofilm formation. *MRS Bull.* 36, 347–355
52. Flemming, H.-C. et al. (2000). *In Cohesiveness in biofilm matrix polymers. In Community Structure and Co-operation in Biofilms*, D.G. Allison et al., eds. (Cambridge University Press), pp. 87–106
53. Regiel-Futyr, A. et al. (2017) Bioinorganic antimicrobial strategies in the resistance era. *Coord. Chem. Rev.* 351, 76–117
54. Li, X. et al. (2015) Control of nanoparticle penetration into biofilms through surface design. *Chem. Commun.* 51, 282–285
55. Mitzel, M.R. et al. (2016) Hydrophobicity of biofilm coatings influences the transport dynamics of polystyrene nanoparticles in biofilm-coated sand. *Water Res.* 92, 113–120
56. Harper, R.A. et al. (2019) Diminishing biofilm resistance to antimicrobial nanomaterials through electrolyte screening of electrostatic interactions. *Colloids Surfaces B Biointerf.* 173, 392–399
57. Mitzel, M.R. and Tufenkji, N. (2014) Transport of industrial PVP-stabilized silver nanoparticles in saturated quartz sand coated with *Pseudomonas aeruginosa* PAO1 biofilm of variable age. *Environ. Sci. Technol.* 48, 2715–2723
58. Adeleye, A.S. et al. (2014) Influence of extracellular polymeric substances on the long-term fate, dissolution, and speciation of copper-based nanoparticles. *Environ. Sci. Technol.* 48, 12561–12568
59. Lowry, G.V. et al. (2012) Transformations of nanomaterials in the environment. *Environ. Sci. Technol.* 46, 6893–6899
60. Bertoglio, F. et al. (2018) Treatment of biofilm communities: an update on new tools from the nanosized world. *Appl. Sci.* 8, 845
61. Benoit, D.S.W. and Koo, H. (2016) Targeted, triggered drug delivery to tumor and biofilm microenvironments. *Nanomedicine* 11, 873–879
62. Fleming, D. and Rumbaugh, K. (2018) The consequences of biofilm dispersal on the host. *Sci. Rep.* 8, 10738
63. Zhang, R. et al. (2016) Antifouling membranes for sustainable water purification: strategies and mechanisms. *Chem. Soc. Rev.* 45, 5888–5924
64. Banerjee, I. et al. (2011) Antifouling coatings: recent developments in the design of surfaces that prevent fouling by proteins, bacteria, and marine organisms. *Adv. Mater.* 23, 690–718
65. Mihai, M.M. et al. (2018) Nanocoatings for chronic wound repair – modulation of microbial colonization and biofilm formation. *Int. J. Mol. Sci.* 19, 1179
66. Radulescu, M. et al. (2016) Silver nanocoatings for reducing the exogenous microbial colonization of wound dressings. *Materials (Basel)* 9, 345
67. Forier, K. et al. (2014) Lipid and polymer nanoparticles for drug delivery to bacterial biofilms. *J. Control. Release* 190, 607–623
68. Li, C. et al. (2013) Preparation and characterization of flexible nanoliposomes loaded with daptomycin, a novel antibiotic, for topical skin therapy. *Int. J. Nanomedicine* 8, 1285
69. Landis, R.F. et al. (2017) Cross-linked polymer-stabilized nanocomposites for the treatment of bacterial biofilms. *ACS Nano* 11, 946–952
70. Zhu, X. et al. (2014) Nanomedicine in the management of microbial infection – Overview and perspectives. *Nano Today* 9, 478–498
71. Bulbake, U. et al. (2017) Liposomal formulations in clinical use: an updated review. *Pharmaceutics* 9, 12
72. Liu, Y. et al. (2019) Nanotechnology-based antimicrobials and delivery systems for biofilm-infection control. *Chem. Soc. Rev.* 48, 428–446
73. Liu, Y. et al. (2018) Nanocarriers with conjugated antimicrobials to eradicate pathogenic biofilms evaluated in murine in vivo and human ex vivo infection models. *Acta Biomater.* 79, 331–343
74. Radovic-Moreno, A.F. et al. (2012) Surface charge-switching polymeric nanoparticles for bacterial cell wall-targeted delivery of antibiotics. *ACS Nano* 6, 4279–4287
75. Boda, S.K. et al. (2015) Cytotoxicity of ultrasmall gold nanoparticles on planktonic and biofilm encapsulated Gram-positive staphylococci. *Small* 11, 3183–3193
76. Barros, C. et al. (2018) Biogenic nanosilver against multidrug-resistant bacteria (MDRB). *Antibiotics* 7, 69
77. Tang, S. and Zheng, J. (2018) Antibacterial activity of silver nanoparticles: structural effects. *Adv. Healthc. Mater.* 7, 1701503

78. Ballottin, D. et al. (2017) Antimicrobial textiles: Biogenic silver nanoparticles against *Candida* and *Xanthomonas*. *Mater. Sci. Eng. C* 75, 582–589
79. Ballottin, D. et al. (2016) Elucidating protein involvement in the stabilization of the biogenic silver nanoparticles. *Nanoscale Res. Lett.* 11, 313
80. Fabrega, J. et al. (2009) Interactions of silver nanoparticles with *Pseudomonas putida* biofilms. *Environ. Sci. Technol.* 43, 9004–9009
81. Choi, O. et al. (2010) Interactions of nanosilver with *Escherichia coli* cells in planktonic and biofilm cultures. *Water Res.* 44, 6095–6103
82. Sheng, Z. and Liu, Y. (2011) Effects of silver nanoparticles on wastewater biofilms. *Water Res.* 45, 6039–6050
83. Shintani, H. (2004) Modification of medical device surface to attain anti-infection. *Trends Biomater. Artif. Organs* 18, 1–8
84. Neoh, K.G. and Kang, E.T. (2011) Combating bacterial colonization on metals via polymer coatings: relevance to marine and medical applications. *ACS Appl. Mater. Interfaces* 3, 2808–2819
85. Singh, B.R. et al. (2015) Mycofabricated biosilver nanoparticles interrupt *Pseudomonas aeruginosa* quorum sensing systems. *Sci. Rep.* 5, 13719
86. Srinivasan, R. et al. (2017) Exploring the anti-quorum sensing and antibiofilm efficacy of phytol against *Serratia marcescens* associated acute pyelonephritis infection in Wistar rats. *Front. Cell. Infect. Microbiol.* 7, 498
87. Naik, K. and Kowshik, M. (2014) Anti-quorum sensing activity of AgCl-TiO₂ nanoparticles with potential use as active food packaging material. *J. Appl. Microbiol.* 117, 972–983
88. Al-Shabib, N.A. et al. (2016) Biogenic synthesis of zinc oxide nanostructures from *Nigella sativa* seed: Prospective role as food packaging material inhibiting broad-spectrum quorum sensing and biofilm. *Sci. Rep.* 6, 1–16
89. Zaroni, M. et al. (2016) Antifouling activity of enzyme-functionalized silica nanobeads. *Biotechnol. Bioeng.* 113, 501–512
90. Habimana, O. et al. (2018) One particle, two targets: A combined action of functionalised gold nanoparticles, against *Pseudomonas fluorescens* biofilms. *J. Colloid Interface Sci.* 526, 419–428
91. Sutherland, I. (2001) The biofilm matrix – an immobilized but dynamic microbial environment. *Trends Microbiol.* 9, 222–227
92. Serra, D.O. et al. (2013) Cellulose as an architectural element in spatially structured *Escherichia coli* biofilms. *J. Bacteriol.* 195, 5540–5554
93. Rohde, H. et al. (2010) Structure, function and contribution of polysaccharide intercellular adhesin (PIA) to *Staphylococcus epidermidis* biofilm formation and pathogenesis of biomaterial-associated infections. *Eur. J. Cell Biol.* 89, 103–111
94. Franklin, M.J. et al. (2011) Biosynthesis of the *Pseudomonas aeruginosa* extracellular polysaccharides, alginate, Pel, and Psl. *Front. Microbiol.* 2, 1–16
95. Colvin, K.M. et al. (2012) The Pel and Psl polysaccharides provide *Pseudomonas aeruginosa* structural redundancy within the biofilm matrix. *Environ. Microbiol.* 14, 1913–1928
96. Conrad, A. et al. (2003) Fatty acids of lipid fractions in extracellular polymeric substances of activated sludge flocs. *Lipids* 38, 1093–1105
97. Romero, D. et al. (2011) An accessory protein required for anchoring and assembly of amyloid fibres in *B. subtilis* biofilms. *Mol. Microbiol.* 80, 1155–1168
98. Romero, D. et al. (2010) Amyloid fibers provide structural integrity to *Bacillus subtilis* biofilms. *Proc. Natl. Acad. Sci. U. S. A.* 107, 2230–2234
99. Paramonova, E. et al. (2009) Hyphal content determines the compression strength of *Candida albicans* biofilms. *Microbiology* 155, 1997–2003
100. Okshevsky, M. et al. (2015) Extracellular DNA as a target for biofilm control. *Curr. Opin. Biotechnol.* 33, 73–80
101. van Schaik, E.J. et al. (2005) DNA binding: a novel function of *Pseudomonas aeruginosa* type IV pili. *J. Bacteriol.* 187, 1455–1464
102. Kobayashi, K. and Iwano, M. (2012) BslA(YuaB) forms a hydrophobic layer on the surface of *Bacillus subtilis* biofilms. *Mol. Microbiol.* 85, 51–66
103. Kulp, A. and Kuehn, M.J. (2010) Biological functions and biogenesis of secreted bacterial outer membrane vesicles. *Annu. Rev. Microbiol.* 64, 163–184
104. Okshevsky, M. and Meyer, R.L. (2015) The role of extracellular DNA in the establishment, maintenance and perpetuation of bacterial biofilms. *Crit. Rev. Microbiol.* 41, 341–352
105. Das, T. et al. (2013) The roles of extracellular DNA in the structural integrity of extracellular polymeric substance and bacterial biofilm development. *Environ. Microbiol. Rep.* 5, 778–786
106. Branda, S.S. et al. (2006) A major protein component of the *Bacillus subtilis* biofilm matrix. *Mol. Microbiol.* 59, 1229–1238
107. Terra, R. et al. (2012) Identification of *Bacillus subtilis* SipW as a bifunctional signal peptidase that controls surface-adhered biofilm formation. *J. Bacteriol.* 194, 2781–2790
108. Hogley, L. et al. (2013) BslA is a self-assembling bacterial hydrophobin that coats the *Bacillus subtilis* biofilm. *Proc. Natl. Acad. Sci. U. S. A.* 110, 13600–13605
109. Solano, C. et al. (2002) Genetic analysis of *Salmonella enteritidis* biofilm formation: critical role of cellulose. *Mol. Microbiol.* 43, 793–808
110. Limoli, D.H. et al. (2015) Bacterial extracellular polysaccharides in biofilm formation and function. *Microbiol. Spectr.* 3, <https://doi.org/10.1128/microbiolspec.MB-0011-2014>
111. Yang, L. et al. (2007) Effects of iron on DNA release and biofilm development by *Pseudomonas aeruginosa*. *Microbiology* 153, 1318–1328